

DOVA-FLEX 905 (C2TE-S1)

C2TE-S1

EN 12004

EUROPEAN NORM

High performance cementitious
flexible tile adhesive



ISO 9001:2015
CERTIFIED
QUALITY MANAGEMENT SYSTEM
970424A



ISO 14001:2015
CERTIFIED
ENVIRONMENTAL MANAGEMENT SYSTEM
970424B



ISO 45001:2018
CERTIFIED
OCCUPATIONAL HEALTH & SAFETY
MANAGEMENT SYSTEM
970424C



DOVA-FLEX 905 (C2TE-S1)

C2

High performance cementitious flexible tile adhesive

What is this product?

High performance mortar-glue with additives to increase resistance and give a high grade of elasticity and impermeability.

Indicated for low absorption coverages: Porcelains, ceramics, marble, big size ceramics and heated floors.



Technical data sheet	
Aspect	Grey or White Powder
Presentation	20 kgs and 25 kgs bag
Coat thickness in walls	from 2 to 6 mm
Coat thickness in floors	from 5 to 10 mm
Output in walls	from 3 to 3,5 kgs/m ²
Output in floors	from 7 to 8 kgs/m ²
Mix water	6,5-7 litres per each 25 kgs
Open time according to UNE EN 1346	30 minutes
Rectification time	15 minutes
Initial adherence according to UNE EN 1348	2,1 N/mm ²
Adherence after water immersion according to UNE EN 1348	1,4 N/mm ²
Adherence after frost cycle according to UNE 1348	1,3 N/mm ²
Adherence after aging through heat UNE 1348	1,8 N/mm ²
Fire reaction	A1
Waiting time for rejoinment	4-8 hours
Slip in vertical wall UNE EN 1308	< 0,5 mm
Temperature during application	min 5°C, max 32°C
Paste density	1,65 gr/cm ³
Stockage (from manufacturing date, under cover, in a dry place)	12 months

Technical Data Sheet (TDS)



DOVA-FLEX 905 (C2TE-S1)



High performance cementitious flexible tile adhesive

Characteristics

Monocomponent.
 Slip resistant.
 Thin coat application.
 High frost resistance and high impermeability grade.
 Manufactured from synthetic resins plastifiers and thickeners.

How to prepare?

1. Pour the water first and then, the mortar-glue.
2. Mix in bowls in an approximated proportion of 6 litres each 25 kgs.
3. It is very important to not add more water than recommended, because physical and chemical conditions would be then, reduced.
4. Mix by hand or with a mixer machine (better slow, 500 rpm) until getting a creamy paste.
5. Let it repose 5 minutes for the additives to act correctly and then mix again before use.
6. Never add more water after the paste settles.

How to use?

Substrates must be clean and dry.
 Extend the product with the smooth part of the trowel to ensure a complete contact with the substrate.
 Use the dented trowel (no. 6-8) in 1,5 – 2 m2 squares.
 Check that no surfacial film is formed over the adhesive.
 In such a case, it's enough to pass the trowel again with some fresh product.
 Place the ceramic leaving 2-3 mm joints.

Composition

White / Grey cement.
 Siliceous soils.
 Redispensible additives and resins.

Precautions

Product components are not toxic.
 It must be worked with gloves, avoid powder inhalation and contact with eyes and skin.
 Keep away from children or animals.

First Aid

Skin: Wash with plenty of water
 Eyes: Wash with plenty of water
 Ingestion: Rinse with water and drink plenty of water

This technical data is written according to our knowledge and essays and doesn't assume any commitment. It's on customer's responsibility the admission and control in the distributor's warehouse or construction, as well as the election of the product to be used on each case. Manufacturer's responsibility is limited to manufacturing defects and for the value of the merchandise because it's out of his control the material election and the working conditions. Technical data for 2023.

We recommend:

To leave 3 mm expansion joints in the extremes of the walls.
 For floors, leave 6 mm perimeter joints.

Where to use?

Ceramic materials placing, for walls and floors, for interior and exterior.
 Substrates: Concrete, cement, cement-lime mortar, cement floors, heated floors, pools, gypsum board walls.
 Substrates must be solid, clean and dry without cracks or deformations.

Technical Data Sheet (TDS)



DOVA-FLEX 905 (C2TE-S1)



High performance cementitious flexible tile adhesive



Technical Data Sheet (TDS)



ISO 9001:2015
CERTIFIED
QUALITY MANAGEMENT SYSTEM
970424A



ISO 14001:2015
CERTIFIED
ENVIRONMENTAL MANAGEMENT SYSTEM
970424B



ISO 45001:2018
CERTIFIED
OCCUPATIONAL HEALTH & SAFETY
MANAGEMENT SYSTEM
970424C



DOVA-FLEX 905 (C2TE-S1)



High performance cementitious
flexible tile adhesive



Makarios III Avenue & Vyronos, P.Lordos Center,
Block B, 2nd floor, office 203, 3105 Limassol, Cyprus.

sales@bodovaltd.com

<https://www.bodovaltd.com/>



Technical Data Sheet (TDS)



ISO 9001:2015
CERTIFIED
QUALITY MANAGEMENT SYSTEM
970424A



ISO 14001:2015
CERTIFIED
ENVIRONMENTAL MANAGEMENT SYSTEM
970424B



ISO 45001:2018
CERTIFIED
OCCUPATIONAL HEALTH & SAFETY
MANAGEMENT SYSTEM
970424C

