



BODOVA LTD.

Raw Gypsum Natural Gypsum

Uses of Natural Gypsum

- White Cement
- Plaster of Paris
- Agriculture Gypsum
- Gypsum Block
- Gypsum Adhesive Compound
- Gypsum Boards

Packing in bulk.

Parameters	Method	Unit	Result
Calcium as CaO	ASTM C 471 M	%	32.27
Magnesium as MgO	ASTM C 471 M	%	1.3
Silica as SiO ₂	ASTM C 25	%	0.84
Iron as Fe ₂ O ₃	ASTM C 25	%	0.03
Aluminum as Al ₂ O ₃	ASTM C 25	%	0.04
Combined water (215 – 230 deg C)	ASTM C 471 M	%	19.05
Total Sulphate as SO ₃	ASTM C 471 M	%	44
Chloride as NaCl #	ASTM C 471 M	%	<0.005
Moisture (Free Water)	ASTM C 471 M	%	0.06
Purity Based Total SO ₃	ASTM C 25	%	94.62

Gypsum Sizes We produce natural gypsum in these sizes:	00-5 mm
	0025 mm
	05-25 mm
	00-50 mm
	20-50 mm
	50-100 mm



Raw Gypsum



Raw Gypsum

Natural Gypsum



Makarios III Avenue & Vyronos, P.Lordos Center,
Block B, 2nd floor, office 203, 3105 Limassol, Cyprus.

sales@bodovaltd.com

<https://www.bodovaltd.com/>



Raw Gypsum

